

Марка стали	C	Cr	V	Mo	W	Co			Твердость
CPM 121 rex	3,4	4,0	9,5	5,0	10,0	9,0			68
CPM 125 V	3,3	14,0	12,0	2,5	-	-			63
M398	2.7	20.0	7.2	1.0	0.7	-			65
K390	2.5	4.0	9.0	4.0	1.0	2.0			65
M390	1.9	20.0	4.0	1.0	0.6	-			
Elmax	1.72	17.8	3.0	1.0	0.11	-			61-62
S390	1.64	4.8	4.8	2.0	10.4	8.0			66-67
X12мф	1.6	12	0.3	0.6	-	-			
K110	1.55	11.8	0.95	0.8	-	-			61-62
X12ф1	1.35	11,7	0,8	-	-	-			
CPR	1.2	12.0	1.7	1.4	2.5	-			64-65
PGK	1,15	8,5	1,95	1,5	1,55	-			62-63
K340	1.1	8.3	0.5	2.1	-	-			64-65
N690	1.08	17.30	0.1	1.1	-	1.5			61-62
P6м5	0.85	4.1	1.9	5.05	6.0	-			(мехпила)